

TEST REPORT/試験報告書

Article No./品番/货号	PC-16	Composition/混率/成分	C100%
Cuttable With/有効幅	145cm	Weight/目付/克重	285g/sqm
Density&Yarn Count /密度&番手/密度&纱织	40/2*20/2 118*65	Organization/組織	twill
HS CODE/海关编码	5209320000		

Test Items/試験項目	Classification/区分	Test Result/試験結果						
		1 10	2 21	3 68	4 89	5 99		
Light/耐光	JIS L 0842	more than 4	4	3-4	more than 4	more than 4		
Washing/洗い/洗滌	JIS L 0844 A-2	color change/変色	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5
			nylon/ナイロン/尼龙	4-5	4-5	4-5	4-5	4-5
liquid/液体	4	4-5	4-5	4	4			
Dry Cleaning ドライ/干洗	JIS L 0860 A-1	color change/変色	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	4-5	4-5	4-5	4-5	4-5	
		liquid/液体	4	3-4	4-5	4-5	4-5	
Perspiration/汗	JIS L 0848	color change/変色	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5
			nylon/ナイロン/尼龙	4-5	4-5	4-5	4-5	4-5
		color change/変色	4-5	4-5	4-5	4-5	4-5	
staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5		
	nylon/ナイロン/尼龙	4-5	4-5	4-5	4-5	4-5		
Rubbing/摩擦	JIS L 0849 TYPE2	Dry/乾摩擦/干摩擦	4-5	4-5	4	4	4	
		Wet/湿摩擦	3	3	2-3	2-3	2	
Water/水洗	JIS L 0844 A-2	color change/変色						
		staining	cotton/棉					
nylon/ナイロン/尼龙								
Perspiration & Light 汗耐光	JIS L 0888 B acid & alkali	acid/酸性						
		alkali/アルカリ/碱性						
Dimensional Change (%) 寸法变化率/缩率	JIS L 0217 103 line (タンブラー/烘干)	warp/タテ/经向					0.0	
		weft/ヨコ/纬向					-0.8	
	JIS L 1096 H-2 (プレス/熨烫)	warp/タテ/经向						
		weft/ヨコ/纬向						
	JIS L 1096 J-1 (タンブラー/烘干)	warp/タテ/经向						
		weft/ヨコ/纬向						
Tear Strenght (N) 引裂き/撕裂强度	JIS L1096 pendulum	warp/タテ/经向	23.1					
		weft/ヨコ/纬向	28.0					
Strenght(mm) 縫目滑脱/滑脱	JIS L 1096 B LOADING ON 117.7N	warp/タテ/经向	0.9					
		weft/ヨコ/纬向	0.9					
Fiber Composition 混率/成份	JIS L 1030							

Care Instruction/洗濯注意事項/洗滌注意事項:
MACHINE WASH COLD/低温水洗い/低温水洗
TUMBLE DRY LOW/低温乾燥/低温烘干
DRY CLEAN/ドライクリーニング可 /可干洗
COOL IRON/低温アイロン/低温熨烫
NO BLEACH/漂白不可

高密のため摩耗した針使用は洗い後裏に花咲きが起こります。（高密のため生地地糸切れ）必ず針とミシン調整必要。ボールポイントの針使用をお勧めします。長時間水に漬けておいたり、濡れたまま放置しないで、洗濯後はすばやく干してください。移染しやすいので他の物と分けて洗ってください。湿った状態や、着用中の摩擦により他の物に移染する恐れがありますので、着用には注意して下さい。

高密度面料在缝纫针过度磨损的情况下，成衣水洗后，面料背面会有纱线起毛现象。（高密度面料使用磨损缝纫针缝之后会有断线现象）所以缝针和机器要做调整。建议使用圆头针用来缝制。请不要长时间浸在水里以及湿的状态放置，洗涤后要快速晾干。因为容易发生移染现象，所以请与别的衣服分开洗涤。衣物湿的状态或者穿着中产生摩擦也会发生移染的现象。请穿着时要注意。

it easy to pilling and yarn broken by overusing the worn sewing needle after washing ,so sewing needle and machine is suggested to adjust and ball point needle is recommend.Pls avoid soaking for a long time,and dry it right after washing. To avoid staining,pls wash separately. In addition, staining may happen due to wetting and rubbing. Pls more attention in daily use.