

TEST REPORT/試験報告書

Article No./品番/货号	AP-249	Composition/混率/成分	C65% N35%
Cutable With/有効幅	145cm	Weight/目付/克重	106g/sqm
Density&Yarn Count /密度&番手/ 密度&纱	50SX70D 166X115	Organization/組織	POPLIN
HS CODE/海关编码	5210310000		

Test Items/試験項目	Classification/区分	Test Result/試験結果						
		1 09	2 22	3 88	4 89	5 99		
Light/耐光	JIS L 0842	3	3-4	3-4	3-4	3-4		
Washing/洗い/洗濯	JIS L 0844 A-2	color change/変色	4-5	4-5	4-5	4	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4	4	4	4
			nylon/ナイロン/尼龙	4-5	4	3-4	4	3-4
Dry Cleaning ドライ/干洗	JIS L 0860 A-1	color change/変色	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	4-5	4-5	4-5	4-5	4-5	
		liquid/液体						
Perspiration/汗	JIS L 0848	color change/変色	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5
			nylon/ナイロン/尼龙	4-5	4-5	4-5	4-5	4-5
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5
nylon/ナイロン/尼龙	4-5		4-5	4-5	4-5	4-5		
Rubbing/摩擦	JIS L 0849 TYPE2	Dry/乾摩擦/干摩擦	4-5	4-5	4	3-4	4	
		Wet/湿摩擦	4-5	3-4	2-3	2	3	
Water/水洗	JIS L 0844 A-2	color change/変色						
		staining	cotton/棉					
			nylon/ナイロン/尼龙					
Perspiration & Light 汗耐光	JIS L 0888 B	acid/酸性	4-5	4	4-5	4	4	
		alkali/アルカリ/碱性	4	4	4-5	4	4	
Dimensional Change (%) 寸法変化率/縮率	JIS L 0217 103 tumble (タンブラー/烘干)	warp/タテ/経向	-0.8					
		weft/ヨコ/緯向	-0.3					
	JIS L 1096 H-2 (プレス/熨燙)	warp/タテ/経向	0.0					
		weft/ヨコ/緯向	0.2					
	JIS L 1096 J-1 (タンブラー/烘干)	warp/タテ/経向						
	weft/ヨコ/緯向							
Tear Strenght (N) 引裂き/撕裂強度	JIS L1096 D METHOD	warp/タテ/経向		8.73				
		weft/ヨコ/緯向		12.8				
Strenght(mm) 縫目滑脱/滑脱	JIS L 1096 B LOADING ON 117.7N	warp/タテ/経向		1.1				
		weft/ヨコ/緯向		1.0				
Water repellency	original					4.4.4		
	after 3 times washing					3.3.3		
	after 10 times washing					3.3.3		
	after 3 times dry cleaning cleaning					3.3.3		
Fiber Composition 混率/成份	JIS L 1030	5 NY34.						

Care Instruction/洗濯注意事項/洗涤注意事項:
MACHINE WASH COLD/低温水洗い/低温水洗
TUMBLE DRY LOW/低温乾燥/低温烘干
DRY CLEAN/ドライクリーニング可 /可干洗
COOL IRON/低温アイロン/低温熨燙
NO BLEACH/漂白不可
DWR (durable water repellent) FINISH/撥水加工/强防水加工
長時間水に漬けておいたり、濡れたまま放置しないで、洗濯後はすばやく干してください。移染しやすいので他の物と分けて洗ってください。素材の特性上、水分や汗、摩擦などにより、色落ちすることがありますので ご着用の際には、十分ご注意ください。ナイロン素材の為、アイロンや芯張りの際、収縮注意。経年による撥水機能の低下の際には、低温あて布でのアイロンやドライヤーの温風をかけますと回復します。
请不要长时间浸在水里以及湿的状态放置，洗涤后要快速晾干。因为容易发生移染现象，所以请与别的衣服分开洗涤。由于此面料的特性，①会因为水/汗摩擦，而掉色，穿着时请注意。②此面料是尼龙混，熨烫和缝制工艺贴衬时注意面料会收缩。③时间久了，防水功能也会变弱，但用低温的垫布用熨斗和用吹风机的中风温度弄下又会恢复了。
Pls avoid soaking for a long time, and dry it right after washing. To avoid staining, pls wash separately. The fabric has the following characteristics, ①It will happen colour fading due to water, perspiration, rubbing; ② It will happen fabric shrinkage when ironing and sticking lining during sewing because of the nylon characteristic; ③DWR function will become weak for long time, while it could be back by using cool iron or dryer, pls more attention.