

TEST REPORT/試験報告書



Article No./品番/货号	ST-243	Composition/混率/成分	P 65% C 33% 2%SP
Cutable With/有効幅	130cm	Weight/目付/克重	180g/sqm
Density&Yarn Count/密度&番手/密度&紗	TC40*TC40+40D	Organization/組織	TWILL
HS CODE/海关编码	5513233100		

Test Items/試験項目	Classification/区分	Test Result/試験結果					
		1 22	2 88	3 99	4 120		
Light/耐光	JIS L 0842	4	≥4	4	4		
Washing/洗い/洗滌	JIS L 0844 A-2	color change/変色	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4	4-5
			NYLON/ナイロン/尼	4-5	4-5	4	4-5
Dry Cleaning ドライ/干洗	JIS L 0860 A-1	color change/変色	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	4-5	4-5	4-5	4-5	
		liquid/液体	4-5	3	3-4	4-5	
Perspiration/汗	JIS L 0848	color change/変色	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	3-4	4	4-5
			NYLON/ナイロン/尼	4-5	3	3	4-5
		color change/変色	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	3	4	4-5
			NYLON/ナイロン/尼	4-5	3-4	3-4	4-5
Rubbing/摩擦	JIS L 0849 TYPE2	Dry/乾摩擦/干摩擦	4	3-4	4	4-5	
		Wet/湿摩擦	4	3	2	4	
Water/水洗	JIS L 0844 A-2	color change/変色	4-5	4-5	4-5	4-5	
		staining	cotton/棉	4-5	4	4-5	4-5
			nylon/ナイロン/尼龙	4-5	3	3	4-5
Perspiration & Light 汗耐光	JIS L 0888 B	acid/酸性	4-5	4-5	4-5	4-5	
sensation(Qmax)	Thermal Lab method					0.448	
Absorbing propert(Second)/点点法	JIS L 1096A					2	
Quick drying(minute)/快 速吸干	JIS L 1096A					34	
Dimensional Change (%) 寸法变化率/缩率	tumble (タンブラー/烘 干)	warp/タテ/经向		-0.7			
		weft/ヨコ/纬向		0.3			
	JIS L 1096 H-2 (プレス/熨烫)	warp/タテ/经向			-0.3		
		weft/ヨコ/纬向			0.3		
	JIS L 1096 J-1 (タンブラー/烘干)	warp/タテ/经向			-0.5		
		weft/ヨコ/纬向			-0.2		
Tear Strenght (N) 引裂き/撕裂强度	JIS L1096 D METHOD	warp/タテ/经向	17.4				
		weft/ヨコ/纬向	9.89				
Strenght(mm) 縫目滑脱/滑脱	JIS L 1096 B LOADING ON 117.7N	warp/タテ/经向	1.0				
		weft/ヨコ/纬向	0.7				
Fiber Composition 混率/成份						ester 62.1 Cotto n 33.1 Polyur ethan	
PH			4.7				

Antibacterial/抗菌	JIS L 1902:2015 Textiles- Determination of antibacterial activity and efficacy of textile products (Staphylococcus aureus NBRC	Not washed /未洗	mediately after inoculation/立即接	5.8*		
		er 18 hours incubation/培养18小时				
		10 cycles /10回	mediately after inoculation/立即接	5.8*		
			er 18 hours incubation/培养18小时			

Care Instruction/洗濯注意事項/洗涤注意事项:

MACHINE WASH COLD/低温水洗い/低温水洗

TUMBLE DRY LOW/低温乾燥/低温烘干

DRY CLEAN/ドライクリーニング可 /可干洗

COOL IRON/低温アイロン/低温熨烫

NO BLEACH/漂白不可

長時間水に漬けておいたり、濡れたまま放置しないで、洗濯後はすばやく干してください。移染しやすいので他の物と分けて洗ってください。素材の特性上、水分や汗、摩擦などにより、色落ちすることがありますので着用の際には、十分ご注意ください。ナイロン素材の為、アイロンや芯張りの際、収縮注意。経年による撥水機能の低下の際には、低温あて布でのアイロンやドライヤーの温風をかけますと回復します。

请不要长时间浸在水里以及湿的状态放置，洗涤后要快速晾干。因为容易发生移染现象，所以请与别的衣服分开洗涤。由于此面料的特性，会因为水/汗摩擦，而掉色，穿着时请注意；此面料是尼龙混，熨烫和缝制工艺贴衬时注意面料会收缩。时间久了，防水功能也会变弱，但用低温的垫布用熨斗和用吹风机的中风温度弄下又会恢复了。

Pls avoid soaking for a long time, and dry it right after washing. To avoid staining, pls wash separately. The fabric has the following characteristics, ①It will happen colour fading due to water, perspiration, rubbing; ② It will happen fabric shrinkage when ironing and sticking lining during sewing because of the nylon characteristic; ③DWR function will become weak for long time, while it could be back by using cool iron or dryer, pls more attention.