

TEST REPORT/試験報告書

GRANTEX®
F A B R I C

Article No./品番/货号	NC-104	Composition/混率/成分	C61% N39%
Cutable With/有効幅	145cm	Weight/目付/克重	151g/sqm
Density&Yarn Count 密度&番手/密度&纱支	70D/2*C30S/2 167*58	Organization/組織/規格	plain/平織/平纹
HS CODE/HSコード/ 海关编码	5210310000		

Test Items/試験項目	Classification/区分	Test Result/試験結果							
		15	22	24	55	89	99		
Light/耐光	JIS L 0842	4	4	4	4 or higher	4 or higher	4 or higher		
Washing/洗/洗涤	JIS L 0844 A-2	color change/变色	4-5	4	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5	4-5
			nylon/ナイロン/尼龙	4-5	4-5	4	4-5	4-5	4-5
		liquid/液体			4				
Dry Cleaning ドライ/干洗	JIS L 0860 A-1	color change/变色	4-5	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	4-5	4-5	4-5	4-5	4-5	4-5	
		liquid/液体			4-5				
Perspiration/汗	JIS L 0848	color change/变色	4-5	4-5	4-5	4-5	4-5	4-5	
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5	4-5
			nylon/ナイロン/尼龙	4-5	4-5	4-5	4-5	4-5	4-5
		staining/汚染/沾色	cotton/棉	4-5	4-5	4-5	4-5	4-5	4-5
nylon/ナイロン/尼龙	4-5		4-5	4-5	4	4-5	4-5		
Rubbing/摩擦	JIS L 0849 TYPE2	Dry/乾摩擦/干摩擦	5	5	4-5	4-5	5	5	
		Wet/湿摩擦	4	4-5	4	2-3	2-3	2-3	
Perspiration & Light 汗耐光	JIS L 0888 B acid & alkali	acid/酸性							
		alkali/アルカリ/碱性							
Dimensional Change (%) 寸法变化率/缩率	JIS L 0217 103 line (タンブラー/烘干)	warp/タテ/经向			-5.3		-0.2		
		weft/ヨコ/纬向			-1.0		-0.2		
	JIS L 1096 H-2 (プレス/熨烫)	warp/タテ/经向			0.0				
		weft/ヨコ/纬向			0.0				
	JIS L 1096 J-1 (タンブラー/烘干)	warp/タテ/经向							
		weft/ヨコ/纬向							
Tear Strenght (N) 引裂き/撕裂强度	JIS L1096 D METHOD	warp/タテ/经向	17.4		15.1 or over				
		weft/ヨコ/纬向	16.5		14.6				
Strenght(mm) 縫目滑脱/滑脱	JIS L 1096 B LOADING ON 117.7N	warp/タテ/经向	0.5		0.9				
		weft/ヨコ/纬向	0.7		1.4				
Fiber Composition 混率/成份	JIS L 1030	C60.5 N39.5		C60.7 N39.3					
WATER REPELLENCY	JIS L 1092	original		5.5.5					
		after 3times washing		4.4.4					
		after 3times dry cleaning		5.5.5					

Care Instruction/洗濯注意事項/洗涤注意事项:

MACHINE WASH COLD/低温水洗/低温水洗

TUMBLE DRY LOW/低温乾燥/低温烘干

DRY CLEAN/ドライクリーニング可/可干洗

COOL IRON/低温アイロン/低温熨烫

NO BLEACH/漂白不可

長時間水に漬けておいたり、濡れたまま放置しないで、洗濯後はすばやく干してください。移染しやすいので他の物と分けて洗ってください。湿った状態や、着用中の摩擦により他の物に移染する恐れがありますので、着用には注意して下さい。ナイロン素材の為、アイロンや芯張りの際、収縮注意。経年による撥水機能の低下の際には、低温あて布でのアイロンやドライヤーの温風をかけますと回復します。

不要长时间泡在水里，也不要湿着放置不管，洗完后要迅速晾干。因为容易产生移染，所以请和其他的衣物分开洗涤。如果是潮湿的状态，穿着中因为产生摩擦，有可能把别的衣物染上颜色，所以请一定要注意。因为是尼龙素材，使用熨斗和烫芯衬的时候一定要注意。随着时间的流逝，当防水功能下降时，垫衬布用低温熨斗烫一下或者用吹风机的暖风功能就能恢复。

Don't soak in water for a long time, and don't keep it wet, dry quickly after washing . It is easy to cause staining, please wash it separately from other clothing. If in the wet state, it is easy to stain other clothes because of friction, pls pay attention!Because !

It is nylon material, you must pay attention to the temperature when using irons and fusible linings.

When the water-repellent function drops over the years, it can be restored with a low-temperature iron or the warm function of the hair dryer.